



KLEENGUARD* G10 POWDER-FREE BLUE NITRILE GLOVES PRODUCT SPECIFICATION

SIZE/CATALOG:	X-Small 57370	Small 57371	Medium 57372	Large 57373	X-Large 57374
----------------------	-------------------------	-----------------------	------------------------	-----------------------	-------------------------

REQUIREMENTS:

1. Style

- Blue Nitrile
- Powder Free
- Non-Sterile
- Beaded Cuff
- Textured Fingertips
- Ambidextrous

2. Barrier

- Freedom from holes (e.g. pinholes) at AQL¹ 6.5

3. Strength

Before Aging		After Aging	
Tensile Strength (MPa)	Ultimate Elongation (%)	Tensile Strength (MPa)	Ultimate Elongation (%)
14 min.	500 min.	14 min.	400 min.

As measured by ASTM D412, Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension. Aged according to ASTM D573, Standard Test Method for Rubber – Deterioration in an Air Oven.

4. Dimensions

- Dimensional characteristics at AQL¹ 10.0. Palm widths +/-10.

Palm Width (mm) – nominal values					Thickness (mm)		Length (mm)
<u>X-Small</u>	<u>Small</u>	<u>Medium</u>	<u>Large</u>	<u>X-Large</u>	Palm	Finger	Cuff
70	80	95	110	120	0.06 min	0.06 min	0.06 min
							230 min

As measured by ASTM D6319, Standard Practice for Nitrile – Measurement of Dimensions

5. Packaging

- 100 gloves (90 for XL) per dispenser box.
- 10 dispenser boxes per case.
- Shipping case and inner packaging labeled with product name, size, lot/batch and catalog number

1. AQL levels defined according to ISO 2859-1 for sampling by attributes.

Kimberly Clark Professional*
1400 Holcomb Bridge Road • Roswell, Georgia
(800)255-6401 • www.kcprofessional.com

