



KIMBERLY-CLARK PROFESSIONAL*
 1400 Holcomb Bridge Road
 Roswell, Georgia
 (800) 851-7538

www.kcprofessional.com

KLEENGUARD* G10 Powder-free Arctic Blue Nitrile Gloves

Product Information

Code	Color	Size	Case Count
90095	Blue	XS	200 gloves/pack • 10 packs per case
90096	Blue	S	200 gloves/pack • 10 packs per case
90097	Blue	M	200 gloves/pack • 10 packs per case
90098	Blue	L	200 gloves/pack • 10 packs per case
90099	Blue	XL	180 gloves/pack • 10 packs per case

Packaging: Shipping case and inner packaging labeled with product name, size, lot/batch and catalog number



Style

- Arctic Blue Nitrile
- Food contact approved
- Powder Free
- Non-Sterile
- Beaded Cuff
- Textured Fingertips
- Ambidextrous

Barrier

- Freedom from holes (e.g. pinholes) at AQL¹ 4.0

Strength

Before Aging		After Aging	
Tensile Strength (MPa)	Ultimate Elongation (%)	Tensile Strength (MPa)	Ultimate Elongation (%)
15 min.	500 min.	14 min.	450 min.

As measured by ASTM D412, Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension. Aged according to ASTM D573, Standard Test Method for Rubber – Deterioration in an Air Oven.

Physical Dimensions

- Dimensional characteristics at AQL1 10.0. Palm widths +/-10.

Size	Palm Width (mm)	Thickness (mm)			Length (mm)
		Palm	Finger	Cuff	
XS	70	0.06 min	0.05 min	0.04 min	240 min
S	80	0.06 min	0.05 min	0.04 min	240 min
M	95	0.06 min	0.05 min	0.04 min	240 min
L	110	0.06 min	0.05 min	0.04 min	240 min
XL	120	0.06 min	0.05 min	0.04 min	240 min

As measured by ASTM D6319, Standard Practice for Nitrile – Measurement of Dimensions.

¹ AQL levels defined according to ISO 2859-1 for sampling by attributes.