



KIMBERLY-CLARK PROFESSIONAL\*  
 1400 Holcomb Bridge Road  
 Roswell, Georgia  
 (800) 851-7538

[www.kcprofessional.com](http://www.kcprofessional.com)

## KLEENGUARD\* G10 Grey Nitrile Gloves



### Product Information

Code	Color	Size	Case Count
97820	Blue	XS	150 gloves/pack • 10 packs per case
97821	Blue	S	150 gloves/pack • 10 packs per case
97822	Blue	M	150 gloves/pack • 10 packs per case
97823	Blue	L	150 gloves/pack • 10 packs per case
97824	Blue	XL	140 gloves/pack • 10 packs per case

**Packaging:** Shipping case and inner packaging labeled with product name, size, lot/batch and catalog number

### Style

- Grey Nitrile
- Powder Free
- Non-Sterile
- Beaded Cuff
- Textured Fingertips
- Ambidextrous

### Barrier

- Freedom from holes (e.g. pinholes) at AQL<sup>1</sup> 4.0

### Strength

Before Aging		After Aging	
Tensile Strength (MPa)	Ultimate Elongation (%)	Tensile Strength (MPa)	Ultimate Elongation (%)
28 min.	500 min.	22 min.	450 min.

As measured by ASTM D412, Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension. Aged according to ASTM D573, Standard Test Method for Rubber – Deterioration in an Air Oven.

### Physical Dimensions

- Dimensional characteristics at AQL1 10.0. Palm widths +/-10.

Size	Palm Width (mm)	Thickness (mm)			Length (mm)
		Palm	Finger	Cuff	
XS	70	0.09 min	0.08 min	0.06 min	240 min
S	80	0.09 min	0.08 min	0.06 min	240 min
M	95	0.09 min	0.08 min	0.06 min	240 min
L	110	0.09 min	0.08 min	0.06 min	240 min
XL	120	0.09 min	0.08 min	0.06 min	240 min

As measured by ASTM D6319, Standard Practice for Nitrile – Measurement of Dimensions.

<sup>1</sup> AQL levels defined according to ISO 2859-1 for sampling by attributes.