

Product Data Sheet

Attributes & Properties[◇]

Name:	513H INTREPID® Filtration Media
Color:	White
Basis Weight:	2.00 ounces per square yard Range 1.95 to 2.15 ounces per square yard (67.8 grams / square meter) Range 66.1 to 72.9 grams per square meter
Efficiency:	50 - 52 % Minimum 45.0 % TSI Model 8130 automated filter tester with 0.1 µm count median diameter NaCl particles at 85 liters per minute.
Air Permeability:	170 – 245 cubic feet of air/minute per square foot of media (0.86 – 1.24 cubic meter of air/second per square meter of media) Textest FX 3300 Labotester III
Inside Core: Diameter	3.0 inches (76 millimeters)

[◇] Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.





Attributes & Properties[◇]

513H INTREPID® Filtration Media

page 2 of 2

Roll Length:	860 linear yards (786 linear meters)
Roll Diameter:	28 inches (711 millimeters) <small>estimated</small>
Slit Width Tolerance:	+1/8, -1/8 inch (+3 mm, - 3 mm) <small>Slit width tolerance measured at the outside of the roll, under tension.</small>
Air Entering Side:	The air entering side of the filter media faces the core.
Packaging:	Cardboard headers, full stretch wrap coverage, multiple slit rolls of the same width may be packaged together into a Powerpack

Roll Labeling Information:

Slit Roll Label
Slit roll number
Product name and description
Production date
Basis weight
Slit width
Roll length
Roll weight

Production Reference: PPSU- 00204

Revision: NJZ 08/08/2013

[◇] Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.